Pottery Process

Pots created by the students in the studio



Pots are dried naturally to ensure there is no moisture in the clay body.

(process takes about 1~2 weeks)



Pots (now called greenware) are fired to about 900 degrees celsius to enable stronger body for glazing.



Fired pots (now called bisque wares) are prepared for glazing so that they can be used.



The glazed pots are once again fired to about 1200 ~ 1300 degrees celsius to fuse the glazes with the clay body.



Fired pots are ready for collection. (about $4 \sim 6$ weeks from the time of creation)